

## INFRARED SPECTROSCOPY OF THE MUSCOVITE (SOPRON)–ILLITE (FÜZÉRRADVÁNY) SYSTEM

GUCSIK, A.<sup>1</sup>, GASHAROVA, B.<sup>2</sup>, BIDLÓ, A.<sup>1</sup>, KOVÁCS, G.<sup>1</sup>, HEIL, B.<sup>1</sup> & PATOCSKAI, Z.<sup>1</sup>

<sup>1</sup>Dept. of Soil Sciences, University of West Hungary, Bajcsy Zs. E. u. 4., H-9400 Sopron, Hungary

E-mail: ciklamensopron@yahoo.com

<sup>2</sup>Institute for Synchrotron Radiation, P.O. Box 36040, D-76021 Karlsruhe, Germany

Mid-infrared (MIR) spectral regions of muscovite (Sopron, Hungary) and illite (Füzérradvány, Hungary) samples were measured as KBr pellets with a Globar source and a MCT detector at ANKA, Institute for Synchrotron Radiation (ISS), Forschungszentrum Karlsruhe, Germany. The cut-off of this detector is about 530  $\text{cm}^{-1}$ . Muscovite/illite exhibits MIR spectral features at 552/538 (bending vibration of  $\text{SiO}_4^{4-}$ ), 1030/1038 (stretching vibrations of  $\text{SiO}_4^{4-}$ ), 1661/1664 (bending vibrations of  $\text{H}_2\text{O}$ ), 3475/3481 and 3634/3641 (stretching vibrations of OH group) (Figs. 1A,B). These spectral features mainly show similarities indicating that there is a very strong structural relationship between muscovite and illite. But, in the lower frequencies some differences occur, which might be due to more stretching Si modes involving weakly bonded cations in illite. FIR spec-

trum of Sopron muscovite as reference material for the muscovite-illite system contains ten peaks at 110, 137, 166, 189, 262, 351, 382, 407, 478, and 532  $\text{cm}^{-1}$ . Füzérradvány illite shows eleven peaks at 94, 118, 193, 260, 334, 384, 419, 473, 505, 528, and 544  $\text{cm}^{-1}$ . There are five peaks, which are dominant in both spectra at around 189, 262, 382, and 478  $\text{cm}^{-1}$  (Figs. 1C,D). These peaks also belong to the bending and stretching vibrations (NAVROTSKY, 1994).

### Reference

NAVROTSKY, A. (1994): Physics and chemistry of earth materials. Cambridge: Cambridge University Press, 116 p.




Fig. 1: Mid-infrared (MIR) and far-infrared (FIR) spectroscopic features of muscovite (Sopron: A, C) and illite (Füzérradvány: B, D).